



SAKRET SE 965

Flexible polyurethane sealant



Color

According to color chart

Package Type and Weight

Sausage, 600 ml

Number of units per package

20

Standards and Certifications

Complies with the requirements of Israeli Standard 1536 for sealing materials and ISO 11600.

Tested according to ISO 8339 and ISO 7389.

Work must comply with the guidelines of Israeli Standard 2378 for cladding, Israeli Standard 1555 for cladding and flooring, Israeli Standard 1872 for cladding, and Israeli Standard 5566 for flooring.

Properties and Main Uses

- For filling and sealing expansion joints.
- Especially suitable for application using the "Baranovitch Method."
- For application on walls and floors.
- High adhesion capability to various substrates.
- High resistance to chemicals and abrasion.
- For both interior and exterior use.

Material Composition

Polyurethane resin and special additives.

Typical Consumption

6-8 linear meters per unit, depending on joint width and depth.

Technical Data

Specific Gravity	1.3 g/ml
Hardness according to Shore A	15-25
Elastic modulus	0.15-0.25 MPa.
Elongation	250%
Tensile Strength	1.3 MPa
Shrinkage	More than 70%

*Data refers to laboratory conditions at 23°C ± 2°C and 50% ± 5% relative humidity



Application Method

- The designated substrate must be dry, clean, and free of any elements that may cause application failure.
- Before joint filling, thoroughly clean the face and edges of the tiles.
- SAKRET SE 965 may be applied only after the following time periods have elapsed:
 - After tile installation on walls: 2 days.
 - After tile installation on floors: 7 days
- Apply the material using a suitable gun.
- Fill the joints with a continuous strip, using moderate trigger pressure for uniform filling.
- Smooth the material using an appropriate tool immediately after application.
- Maximum joint dimensions: width 40 mm, depth 20 mm.

General instructions

- Store the product in a shaded, well-ventilated area.
- The material is suitable for use up to 12 months from the production date, provided it is stored in its original packaging under recommended conditions.
- Permitted application temperature range: 5°C - 35°C.
- Ensure proper ventilation during application.
- Walking on the floor is permitted only 48 hours after completion of SAKRET SE 965 application.
- Before application, a small test area should be applied to assess suitability and desired color.
- Due to material sensitivity, prolonged exposure to sunlight (UV rays) may cause color variations.
This does not affect the material's properties.
- Workability time may vary depending on environmental conditions at the time of application.
- Do not apply under extreme climatic conditions (heatwave, rain, winds).
- Ensure compliance with relevant standards.
- Before starting work, consult company representatives for guidelines and technical specifications.

Warranty

The company's warranty is limited to the integrity and quality of materials only and does not replace the worker's responsibility. The worker must check the product and system's suitability for their needs, compatibility with other materials, and proper execution of the work. We reserve the right to update or change the data and recommendations without advance notice. The worker is responsible for checking the latest updates.

Translation Disclaimer

This product information has been translated from Hebrew to English for convenience only. In case of any discrepancy between the English translation and the original Hebrew language, the Hebrew version shall prevail. Therefore, we recommend relying solely on the information written in Hebrew! Furthermore, before using any product, you should consult the technical department for prior advice and support during use. The company accepts no responsibility for any damage or loss resulting from failure to comply with these instructions.

Updated: 11.2025